

Documenttitel:	Productinfo SCR53 en SCR53C	Creatiedatum:	13-05-2014
Auteur:	P055204: Heidi Giezen	Versienummer:	1
Verantwoordelijke:	Documentbeheerder Customer Service	Publicatiedatum:	22-05-2014



English



Auxiliary products for rotary screen engraving

SCR 53 / 53C

Endring adhesive and catalyst

For glueing endrings into rotary screens.

Two-component adhesive, with good resistance.

SCR 53	White transparent
SCR 53 C	Brown transparent

SCR 53 : SCR 53 C = 1 : 1 (volume parts)
 = 10 : 8 (weight parts)

After mixing apply with spatula onto endring and onto approx. 2 cm scoured screen-ends.

After insertion of endring drying time:

20 °C : 10 hours
 70 °C : 2 hours
 120 °C : 15 minutes
 150 °C : 4-5 minutes

Potlife : 20 minutes

One year

SCR 53	1-kg can
SCR 53 C	0.8-kg can

The data published herein answer to the most recent information at the moment of publishing and are subject to future modifications. SPGPrints reserves the right to modify the construction and the execution of their products at any time without any obligation on their part to modify any equipment delivered before accordingly

Date of issue: May 2014